

Product Information

Enduro Protect, EN50-250

Physical Properties*

DENSITY	49.0 to 53.5 kg/m ³	I.F.D. HARDNESS RANGE (NEWTONS)
TEAR RESISTANCE	180N/m Minimum	IF 40% Minimum 230N
TENSILE STRENGTH	120kPa Minimum	IF 40% Maximum 270N
ELONGATION	110% Minimum	IF25% RECOVERY 80% Minimum
RESILIENCE	50% Minimum	INDENTATION
COMPRESSION SET (75%)	8% Maximum	(SAG) FACTOR 2.4 Minimum

* When tested internally in accordance with the test methods listed in Australian Standard AS2282.0

Available Colours

Salmon

Tested to the following Flammability Standards**

Standard	Description	Result
AS1530/Pt.3	Determination of ignitability, flame spread, Heat evolved and smoke developed.	18/0/0/6
BS5852/Source 5-Mod.	Methods of test for assessment of the ignitability of upholstered seating by smouldering and flaming ignition sources, Source 5.	NI,5 - PASS
CAL 117, Sec.3	Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture	MEETS
F.A.R. 25.853/App.F/Part I	Federal Aviation Regulations - Airworthiness Standards: Transport Category Airplanes – Vertical Burn test.	MEETS
AS/NZS 3744.3	Assessment of the ignitability of upholstered furniture - Ignition source - Match-flame equivalent (Source 2)	NI - PASS

** These test results alone do not assess the fire hazard of the material or the product made from this material under actual fire conditions.

Grade Description

Premium quality, flame retarded, very firm cushioning foam. Incorporating Ultra-Fresh™ for antimicrobial protection.

Typical Applications

Contract and transport seating. Not recommended for stretching and stapling.

Information current as at Nov 2016

Contact Dunlop Foams

447 Foleys Rd, Deer Park, VIC 3023
 Phone: 1800 736 634 or +617 3345 3644 Fax: 1800 736 994
 Email: enquires@dunlopfoams.com.au