

## New Mexico

## **DESCRIPTION**

A full grain distressed wax pull-up leather. Paraffin wax in applied along with a specialized tumbling process to create a unique two-toned effect.

## **SPECIFICATIONS**

Average Hide Size		52 sq. ft. / 4.83 sq. mt.
Thickness		1.0 - 1.1 mm
PERFORMANCE CHAP	ACTERISTICS	
Light Fastness	(AATCC Method 16, Option E)	3 - 4
Tear Strength	(ASTM D4705)	25 lbs.
Flexing Endurance	(ASTM D2097)	Pass
Abrasion	(ASTM D3884)	N/A
Elongation	(ASTM D2211)	30-50% at 50 lbs.
Crocking	(ASTM D5053)	Wet 3: Dry: 4
Breaking Force	(ASTM D2208)	175 lbs.
FLAMMABILITY		
Boston Fire Dept. Code (BFD 1x1) w/Fire Blocker and or Fire Barrier Cloth		Pass
California Technical Bulletin 117		Pass
Cigarette Ignition Resistance	(NFPA 260)	Class 1
California Technical Bulletin 133 w/Fire Blocker and/or Fire Barrier Cloth		Pass

## **CLEANING INSTRUCTIONS**

Natural, aniline leathers have little surface protection. If your aniline leather does become soiled, immediately blot excess liquid with a soft, clean cloth. Then clean the entire area (i.e. the entire seat cushion, arm rest, etc.) with a clean, damp cloth and clear luke warm water, starting from the outside of the spill to the center.

Do not use: Any saddle soaps, oils, abrasives, cleaners, soaps, furniture polish, varnish or ammonia water.

*Please note:* Due to the natural characteristics of this leather, scratches and marks may appear over time. This appearance is the "character" of the natural leather.